

Viapol Modulo Levis Project Mineral CE

Description : plastomeric polymer bitumen membrane BPP, compound in distilled bitumen modified with high molecular weight polymer, reinforced with nonwoven polyester glass stabilized. top face coated with hot-bonded slate granules

Field of Application : top layer, self protected, in a multy-layer waterproofing system

Method of Application : torched on

Applicable Directive : EN 13707

Dangerous Substances : the product does not contain asbestos or tar.

| CHARACTERISTIC | EN DRC | UNIT | VALUE | | TOL |
|--|------------|-------------------|---------|-------|---------|
| Visible Defects | EN 1850-1 | ----- | pass | | ----- |
| Thickness | EN 1849-1 | mm | 4,5 | | pass |
| Areic Mass | EN 1849-1 | kg/m ² | 4,5 | | -10% |
| Width and Length | EN 1848-1 | m | 1,00 | 10,00 | -1% |
| Straightness | EN 1848-1 | mm | max 20 | | pass |
| Max Tensile Force (L / T) | EN 12311-1 | N/5cm | 750 | 550 | -20% |
| Elongation (L / T) | EN 12311-1 | % | 40 | 40 | -15 abs |
| Resistance to Tearing (L / T) | EN 12310-1 | N/5cm | 150 | 150 | pass |
| Resistance to Static Loading | EN 12730-A | kg | 15 | | pass |
| Resistance to Impact | EN 12691 | mm | 900 | | pass |
| Joint Strenght (L / T) | EN 12317-1 | N/5cm | | | npd |
| Peel Resistance of Joint | EN 12316-1 | N/5cm | | | npd |
| Pliability (Cold Flexibility) | EN 1109 | °C | -15 | | pass |
| Pliability (Aged) | EN 1296 | °C | | | npd |
| Uv Ageing (Visible Defects) | EN 1297 | ----- | pass | | ----- |
| Watertightness | EN 1928 | kPa | 60 | | pass |
| Water Vapour Permeability | EN 1931 | μ x 1.000 | 20 | | -20% |
| Water Vapour Permeability (Aged) | EN 1296 | μ x 1.000 | | | npd |
| Flow resistance (New / Aged) | EN 1110 | °C | 120 | 110 | pass |
| Dimensional Stability (L / T) | EN 1107-1 | % | -0,25 | 0,15 | pass |
| Root Resistance | MBP Group | % add | | | npd |
| External Fire Performance | EN 13501-5 | class | F(roof) | | npd |
| Reaction to Fire | EN 13501-1 | class | F | | npd |
| Adhesion of Granules (Mineral Version) | EN 12039 | % | 30 | | pass |

| | | | | | | |
|--------------------|----------------|--|-------|-------|-----|-------|
| Topside Finish | | slate chips/granules (mineral self-protection) | | | | |
| Underside Finish | | thermo-fusible polyethylene film | | | | |
| Pallet Composition | Areic Mass | kg/m ² | 3,5 | 4 | 4,5 | 5 |
| | Rolls x Pallet | n° | ----- | ----- | 20 | ----- |
| Packaging | | shrinkable polyethylene film, on pallet | | | | |
| Additional Info | | " Polymer Bitumen Membrane Info Sheet ", current release | | | | |

technical data declared may vary without previous notice

rev 002 - 08.2013



Vetroasfalto SpA
 Via Pascoli, 3 - 20060 Basiano (MI) - Italy
 tel +39.02.959831 - fax +39.02.95983555
 email: vetroasfalto@vetroasfalto.com
 www.vetroasfalto.com
 Quality Assurance : UNI EN ISO 9001:2008
 Certificate : 0546/CPD-16876

